

Sample Date	45µm	LOI	SO3	S	MgO	Fe2O3	Al2O3	Mn2O3	Total Alkali	Chloride	Insoluble residue	Relative density	Relative water	Strength Index
	%	%	%	%	%	%	%	%	NaEQ%		%		%	%
22-May-24	1.6	-0.1	2.9	0.8	5.9	0.89	13.84	0.22	0.5	<0.001	0.8	2.89	104	105
18-Apr-24	3.1	-0.3	3.1	0.8	5.9	0.85	13.87	0.21	0.5	0.001	0.3	2.87	102	103
20-Mar-24	2.0	-0.8	2.6	0.8	6.0	1.01	14.15	0.20	0.4	<0.001	0.3	2.88	101	104
29-Feb-24	1.6	-0.1	2.6	0.8	5.8	0.92	14.12	0.19	0.4	<0.001	0.2	2.88	101	102
15-Jan-24	1.7	-0.6	2.2	0.8	6.1	0.81	14.39	0.20	0.4	<0.001	0.2	2.91	101	102
19-Dec-23	1.1	-1.0	2.0	0.8	6.1	0.91	14.55	0.20	0.4	<0.001	0.2	2.91	101	112
26-Nov-23	1.3	-0.8	2.5	0.9	6.1	0.85	14.31	0.20	0.5	0.004	0.2	2.89	101	112
10-Oct-23	2.0	-1.0	2.0	0.8	6.1	0.86	14.55	0.19	0.4	<0.001	0.2	2.92	101	111
25-Sep-23	2.5	-0.6	2.7	0.8	6.2	0.70	14.19	0.22	0.4	0.002	0.2	2.89	101	99
04-Aug-23	1.7	-0.8	2.4	0.8	6.2	0.67	14.23	0.24	0.5	0.004	0.2	2.89	101	98
<b>Mean</b>	1.9	-0.6	2.5	0.8	6.0	0.8	14.2	0.2	0.4			2.89	101	105
<b>StdDev</b>	0.6	0.3	0.36	0.02	0.13	0.1	0.2	0.02	0.05			0.02	0.9	5
<b>AS/NZS 3582.2:2016</b>				1.50%	15%		18%			0.10%				
<b>Specifications</b>				Max	Max		Max			Max				
<p>HR Cement Ltd is registered for the production &amp; distribution of cement in accordance with ISO 9001:2015. Eco-cem is tested in accordance with AS / NZS 3582.2:2016. Samples tested as received. This Test Report may not be reproduced except in full.</p> <p>Testing conducted by Cement Australia (Darra, Brisbane, Australia) Nata Accreditation Numbers: 187, 188</p>														
<p><i>DA Chater</i></p> <p>Dave Chater - Technical Manager</p>														
					Issue Date: 01/08/2024					Report ID: HRC-ECO-CEM-099				